

# Technical Data Sheet

77376 - PE/P/Q WHITE RAL 9016

Trade code: 77376

## GENERAL FEATURES

This thermosetting powder contains polyester resins cured with fit curing agents specially selected for their excellent resistance to UV radiation and outdoor weathering.

The powder forms a decorative film with enhanced outdoor resistance.

The Syntha Pulvin-Q were created for coating aluminium components used in architecture and for coating galvanised steel and have all the necessary requirements for approval of the GSB specification (I.152g).

The Syntha Pulvin-Q have also all the necessary requirements for approval of the Qualicoat class 1 category 3 (licence P-0554) specification.

## APPLICATION

Due to its special content the product is particularly suggested for exterior coating.

## ADVISED CYCLES

The surface to be coated must be cleaned from oils, grease or flash rust.

If particular resistance to corrosion or humidity is required, it is suggested the following pretreatment of the surface:

|                      |   |
|----------------------|---|
| for aluminium        | chromate, phospho-chromate conversion (DIN 50939) or other pretreatment Cr-free Qualicoat or GSB approved |
| for steel            | sand blasting or/and iron or zinc phosphatising   |
| for galvanised steel | chromatising  |

## HANDLING AND STORAGE

Store at temperatures lower than 30°C; higher temperatures may damage the powder by causing undesired alterations or blobs.

Storage life in original package: 24 months.

## TECHNICAL DATA

| Code    | Int. Method                               | Range         | Ref. Method          |
|---------|---|---------------|----------------------|
| P/CL092 | Calc. specific gravity(kg/l):             | 1.546 - 1.609 |                      |
| P/CL120 | Non volatile content(w/w)(%) 3h at 105 °C | 100.0 - 100.0 | UNI EN ISO 3251      |
| P/CL125 | Non volatile content(v/v)(%)              | 100.0 - 100.0 |                      |
| P/CL143 | 1µm Theor. spread. rate (m2/kg):          | 622 - 647     |                      |
| P/CL210 | Water content (%)                         | 0.0 - 0.0     |                      |
| P/YC060 | Particle size dist. <32µm (%)             | 45 - 47       |                      |
| P/YC120 | Particle size dist. <63µm (%)             | 90 - 92       |                      |
| P/CS010 | Dry film thickness(microns):              | 60 - 80       | UNI ISO 2178         |
| P/CC050 | Gloss 60° :                               | 84.0 - 89.0   | UNI EN ISO 2813:2014 |

## WAYS OF APPLICATION

Apply with guns with negative terminal (60/80KV) or triboelectric guns automatically or manually.

It is advised to apply the product in layers with the thickness of 60-80 microns and to stove at 180°C for 15 minutes (temperature of the support).

For stoving of the Polyester-Q Cat. 3 products it is possible to use the following combinations of time and temperature:

|               |                                    |
|---------------|------------------------------------|
| 8-12 minutes  | 200°C (temperature of the support) |
| 10-20 minutes | 190°C (temperature of the support) |
| 15-25 minutes | 180°C (temperature of the support) |
| 20-40 minutes | 170°C (temperature of the support) |

Rev. Date 5/10/2020 Page n. 1 of 3

### INVER SpA con Unico Socio

Via di Corticella, 205 - 40128 Bologna (BO) - ITALY  
Manufacturing and R&D Labs: Via Marconi 10/A - 40061 Minerbio (BO) ITALY  
Ph. +39 051 638 0411 - www.inver.com - inver@sherwin.com  
Inver SpA is a member of The Sherwin-Williams Company

**SHERWIN-WILLIAMS**

# Technical Data Sheet

77376 - PE/P/Q WHITE RAL 9016

For stoving use the given indications.

For naval application, maximum film thickness limitation according to Module B certificate MEDB00001R1.

## TECHNOLOGICAL FEATURES AND RESISTANCE TESTS

|                  |                          |
|------------------|--------------------------|
| The support used | aluminium panel (ALQ-36) |
| Thickness        | 60 microns               |
| Stoving          | 15 minutes at 180°C      |

Chemical resistance test by immersing for 48 hours at indoor temperature into:

|                              |                       |
|------------------------------|-----------------------|
| hydrochloric acid 10 %       | film is intact        |
| Nitric acid 30 %             | matt, but washing off |
| Sulphuric acid 10 %          | intact                |
| hydrogen peroxide 40 volumes | intact                |
| ammonium hydroxide 10 %      | intact                |
| ammonium hydroxide 33 %      | intact                |
| sodium hydroxide 5 %         | intact                |
| tartaric acid 5 %            | intact                |
| citric acid 5 %              | intact                |
| lactic acid 5 %              | intact                |
| ethanol                      | intact                |
| N-butanol                    | intact                |
| petroleum ether              | slightly softened     |

The chemical resistance test was carried out on chromatised aluminium.

| Code    | Int. Method                              | Range  | Ref. Method                  |
|---------|--|--|------------------------------|
| P/CM010 | Buchholz indentation test :              | more than 90   | UNI EN ISO 2815              |
| P/CM040 | Erichsen cupping test (mm):              | more than 5  | UNI EN ISO 1520              |
| P/CM050 | Direct impact test (cm.Kg):              | more than 25   | ASTM D 2794; ISO 6272-2:2002 |
| P/CM051 | Reverse impact test(cm.kg):              | more than 25   | ASTM D 2794; ISO 6272-2:2002 |
| P/CM075 | Cylindrical mandrel size 5 :             | does not break   | UNI EN ISO 1519              |
| P/CM100 | Crosscut adhesion (2mm)(GT):             | 00   | UNI EN ISO 2409              |
| P/CM195 | Acetic salt fog test :                   | according to Qualicoat and GSB-International Requirements              |                              |
| P/CM230 | Resistance to humidity : (Humidity test) | 1000 hours later no blistering, indentation along the cross of max 1mm | UNI EN ISO 6270-2:2005       |

## NOTES

Accelerated weathering:

|                       |                        |  |
|-----------------------|------------------------|--|
| 1000 h Xenon-arc test | >= 50% gloss retention | according with Qualicoat cycle (ISO 16474-2) |
| 300 h UV-B test       | >= 50% gloss retention | according with GSB cycle (ISO 16474-3)       |

Rev. Date 5/10/2020 Page n. 2 of 3

### INVER SpA con Unico Socio

Via di Corticella, 205 - 40128 Bologna (BO) - ITALY  
Manufacturing and R&D Labs: Via Marconi 10/A - 40061 Minerbio (BO) ITALY  
Ph. +39 051 638 0411 - www.inver.com - inver@sherwin.com  
Inver SpA is a member of The Sherwin-Williams Company

**SHERWIN-WILLIAMS**

# Technical Data Sheet

77376 - PE/P/Q WHITE RAL 9016

---

## NOTE TO USER

The information contained in this document while based on evidence and reliable methods can not be considered exhaustive.

This information are current to the date of issuance of this data sheet, therefore is under user's responsibility to verify that the data provided on this sheet are current to the date of the product.

The user, under its own responsibility, shall respect all the existing provisions on hygiene and safety and shall verify every time the features and the specific and appropriate way to use the product, cause the respect of the provisions is not under producer's direct control.

The manufacturer does not guarantee nor assume any liability or responsibility for whatsoever harm that might result from a misuse of the product or for damages that have arisen after the product's distribution.