



**GENERAL FEATURES**

This thermosetting powder with epoxy and polyester resins is suggested for polymerisation at low temperature (160°C).  
 The product forms level hard film with good resistance to mechanical damage, detergents, fuels and oils.  
 It is resistant to yellowing caused by the chain stop during stoving.  
 Its chemical resistance results good.

**APPLICATION**

Due to its special content the product has excellent protective and decorative effects. It is suggested particularly for interior coating.

**ADVISED CYCLES**

The surface to be coated must be cleaned from oils, grease or flash rust.  
 If particular resistance to corrosion or humidity is required, it is suggested the following pretreatment of the surface:

for steel	sand blasting or/and iron or zinc phosphatising
for galvanised steel and aluminium	chromatising

**HANDLING AND STORAGE**

Store at temperatures lower than 30°C; higher temperatures may damage the product by causing undesired alterations or blobs.  
 Storage life in original package: 18 months.

**TECHNICAL DATA**

Code	Int. Method	Range	Ref. Method
P/CL092	Calc.specific gravity(kg/l):	1.593 - 1.658	
P/CL120	Non volatile content(w/w)(%) 3h at 105 °C	100.0 - 100.0	UNI EN ISO 3251
P/CL125	Non volatile content(v/v)(%)	100.0 - 100.0	
P/CL143	1µm Theor.spread.rate (m2/kg):	603 - 628	
P/CL210	Water content (%):	0.0 - 0.0	
P/YC060	Particle size dist. <32µ(%):	36 - 46	
P/YC120	Particle size dist. <63µ(%):	74 - 91	

**WAYS OF APPLICATION**

Apply the product with automatic or manual guns with negative terminal (60/80KV) or triboelectric guns.  
 It is advised to apply in layers with the thickness of 90-110 microns and to stove at 170°C for 15 minutes.  
 For stoving of the epoxy polyester BT texture products it is possible to use the following combinations of time and temperature:

10-15 minutes	180°C (temperature of the support)
---------------	------------------------------------

	port)
15-22 minutes	170°C (temperature of the support)
20-30 minutes	160°C(temperature of the support)

For stoving use the given indications.

**TECHNOLOGICAL FEATURES AND RESISTANCE TESTS**

The support used	UNI sheet
Thickness	90 microns
Stoving	15 minutes at 170°C

The hardness test was carried out on zinc phosphatised steel.

Code	Int. Method	Range	Ref. Method
P/CM040	Erichsen cupping test (mm):	more than 3	UNI EN ISO 1520
P/CM050	Direct impact test (cm.Kg):	more than 20	ASTM D 2794; ISO 6272-2:2002
P/CM051	Opposite impact test(cm.kg):	more than 5	ASTM D 2794; ISO 6272-2:2002
P/CM170	Conical mandrel : Bend test	maximum 20mm	UNI EN ISO 6860
P/CM100	Crosscut adhesion (2mm)(GT):	00	UNI EN ISO 2409
P/CM190	Salt fog test :	1000 hours later - indentation along the cross of 3-6 mm	UNI ISO 9227
P/CM230	Resistance to humidity : (Humidity test)	500 hours later - no change	UNI EN ISO 6270-2:2005

**NOTE TO USER**

The information contained in this document while based on evidence and reliable methods can not be considered exhaustive.  
 This information are current to the date of issuance of this data sheet, therefore is under user's responsibility to verify that the data provided on this sheet are current to the date of the product.  
 The user, under its own responsibility, shall respect all the existing provisions on hygiene and safety and shall verify every time the features and the specific and appropriate way to use the product, cause the respect of the provisions is not under producer's direct control.  
 The manufacturer does not guarantee nor assume any liability or responsibility for whatsoever harm that might result from a misuse of the product or for damages that have arisen after the product's distribution.